

MANDARIN STONE

PRODUCT SPECIFICATION

CALACATTA MARBLE

Technical Features	Reference	Average Value
Reaction to Fire	96/603/EC	Class A1
Water Absorption at atmospheric pressure	EN 13755	0.10%
Apparent Density	EN1936	2,680kg/m ³
Open Porosity		0.30%
Water absorption by capillarity	EN 1925	0.66g/m ² .s ^{0.5}
Flexural strength under concentrated load	EN 12372	7.72 MPa
Compressive strength after freezing	EN 12371	48.70 MPa
Abrasion Resistance	EN 1341	19.90 mm
Slip Resistance (Polished Finish) (Dry)	EN 14231	NPD
Slip Resistance (Polished Finish) (Wet)		NPD
Slip Resistance (Honed Finish) (Dry)	EN 14231	NPD
Slip Resistance (Honed Finish) (Wet)		NPD