

# MANDARIN STONE

## **PRODUCT SPECIFICATION** Campione Tumbled Limestone

Technical features - compliant with standards EN 14411 (ISO 13006) annex G group Bia GL

<b>Technical Features</b>	<b>Reference</b>	<b>Average Value</b>
Reaction to Fire	96/603/EC	Class A1
Flexural Strength – Mean Value	EN 12372	19.7MPa
Abrasion Resistance	EN 14157	NPD
Water absorption at atmospheric pressure (by mass)	EN 13755	0.7%
Water absorption at atmospheric pressure (by volume)		NPD
Apparent Density	EN1936	2636kg/m <sup>3</sup>
Slip Resistance Value – Wet	EN 14231	14.25
Slip Resistance Value – Dry		NPD
Open Porosity	EN 1936	0.31%
Flexural strength after freezing	EN 14066	0.115%