

MANDARIN STONE

PRODUCT SPECIFICATION

CLASSIC ST ARBOIS TUMBLED LIMESTONE

Technical features - compliant with standards EN 14411 (ISO 13006) annex G group Bia GL

Technical Features	Reference	Average Value
Reaction to Fire	96/603/EC	Class A1
Flexural Strength – Mean Value	EN 12372	15,73 MPa
Abrasion Resistance	EN 14157	20 mm
Water absorption at atmospheric pressure (by mass)	EN 13755	0,3%
Water absorption at atmospheric pressure (by volume)		NPD
Apparent Density	EN1936	2638 kg/m ³
Slip Resistance Value – Wet	EN 14231	37
Slip Resistance Value – Dry		42
Open Porosity	EN 1936	0,41%
Flexural strength after freezing	EN 14066	-0,04%