

EST / 1989

MANDARIN STONE

PRODUCT SPECIFICATION

DIJON LIMESTONE

Technical Features	Reference	Average Value
Reaction to fire	96/603/EC	Class A1
Density	EN 1936	2,567 g/cm ³
Water absorption	EN 13755	NPD
Flexural Strength	EN 12372	15.90 MPa
Flexural strength after freezing	EN 14066	-0.02 %