

MANDARIN STONE

PRODUCT SPECIFICATION

NERO SLATE RANGE

Technical Features	Reference	Average Value
Reaction to Fire	96/603/EC	Class A1
Flexural Strength – Mean Value	EN 12372	20.50 MPa
Abrasion Resistance	EN 14157	25.40 mm
Water absorption at atmospheric pressure (by mass)	EN 13755	0.41%
Water absorption at atmospheric pressure (by volume)		1.11%
Apparent Density	EN 1936	2.725kg/m ³
Open Porosity	EN 1936	0.90%
Slip Resistance Value – Dry (Riven)	EN 14231	72.00
Slip Resistance Value – Wet (Riven)		48.00