

MANDARIN STONE

PRODUCT SPECIFICATION

Paris Blue Limestone

Technical features - compliant with standards EN 14411 (ISO 13006) annex G group Bia GL

Technical Features	Reference	Average Value
Reaction to Fire	96/603/EC	Class A1
Flexural Strength – Mean Value	EN 12372	12.4 MPa
Abrasion Resistance	EN 14157	23.5mm
Water absorption at atmospheric pressure (by mass)	EN 13755	2.5%
Water absorption at atmospheric pressure (by volume)		2.5%
Apparent Density	EN1936	NPD
Slip Resistance Value – Wet	EN 14231	NPD
Slip Resistance Value – Dry		NPD
Open Porosity	EN 1936	NPD
Flexural strength after freezing	EN 14066	-0.07%