

MANDARIN STONE

PRODUCT SPECIFICATION

Silver Tumbled Travertine

Technical features - compliant with standards EN 14411 (ISO 13006) annex G group Bia GL

Technical Features	Reference	Average Value
Reaction to Fire	96/603/EC	Class A1
Flexural Strength – Mean Value	EN 12372	8.31 MPa
Abrasion Resistance	EN 14157	29.16mm
Water absorption at atmospheric pressure (by mass)	EN 13755	0.67%
Water absorption at atmospheric pressure (by volume)		0.67%
Apparent Density	EN1936	2.47gr/ cm ³
Slip Resistance Value – Wet	EN 14231	NPD
Slip Resistance Value – Dry		NPD
Open Porosity	EN 1936	7.71%
Flexural strength after freezing	EN 14066	NPD