

EST / 1989

MANDARIN STONE

PRODUCT SPECIFICATION

GRIS SLATE

Technical Characteristic	Reference	Average Value
Reaction to fire	96/603/EC	Class AI
Flexural strength - mean value	EN 12372	48.70 MPa
Abrasion resistance	EN 14157	24.60 mm
Water absorption at atmospheric pressure (by mass)	EN 13755	0.35 %
Water absorption at atmospheric pressure (by volume)		0.95 %
Apparent density	EN 1936	2,722 kg/m ³
Open porosity		0.70 %
Slip resistance value - dry (Riven)	EN 14231	68.00
Slip resistance value - wet (Riven)		41.00