

EST / 1989

# MANDARIN STONE

## **PRODUCT SPECIFICATION**

### NERO SLATE

Technical Characteristic	Reference	Average Value
Reaction to fire	96/603/EC	Class AI
Flexural strength – mean value	EN 12372	20.50 MPa
Abrasion resistance	EN 14157	25.40 mm
Water absorption at atmospheric pressure (by mass)	EN 13755	0.41 %
Water absorption at atmospheric pressure (by volume)		1.11 %
Apparent density	EN 1936	2,725 kg/m <sup>3</sup>
Open porosity	EN 1936	0.90 %
Slip resistance value – dry (Riven)	EN 14231	72.00
Slip resistance value – wet (Riven)		48.00