

MANDARIN STONE

PRODUCT SPECIFICATION **CLASSIC LYON PROVENCE STONE**

Technical features - compliant with standards EN 14411 (ISO 13006) annex G group Bia GL

Technical Features	Reference	Average Value
Reaction to Fire	96/603/EC	Class A1
Flexural Strength – Mean Value	EN 12372	11.1 MPa
Abrasion Resistance	EN 14157	NPD
Water absorption at atmospheric pressure (by mass)	EN 13755	NPD
Water absorption at atmospheric pressure (by volume)		NPD
Apparent Density	EN1936	2,625kg/m ³
Slip Resistance Value – Wet	EN 14231	NPD
Slip Resistance Value – Dry		NPD
Open Porosity	EN 1936	2%
Flexural strength after freezing	EN 14066	0.32%